

PSGSG 13-14 / 028	<b>Product Specifications For FIXED ES CONTACTS</b>		Drg. No.	RDDG 435 0517 2020
			Date	13.02.2014
			Product	<b>GSM 245</b>
<b>1.0</b>	<b>Application</b>	: Fixed Contacts for Gas Insulated Switchgear Equipment		
<b>2.0</b>	<b>Configuration</b>	: <ul style="list-style-type: none"> <li>1. Sintered W-Cu (70-30 %), welded (by electron Beam welding process) to the high conductivity copper-Cr alloy.</li> <li>2. Sintered W-Cu (80-20 %)</li> <li>3. Machined to drawing dimensions.</li> </ul>		
<b>3.0</b>	<b>Quantity</b>	: 10 No.s of ES Fixed contact		
<b>4.0</b>	<b>Specifications:</b>	<ul style="list-style-type: none"> <li>1. Dimension Drawings : Refer Drg No. RDDG 435 0517 2020</li> <li>2. Material: : Tungsten-Copper, Cu-Cr alloy</li> </ul> <p><b>(a). W-Cu</b></p> <p>A sintered matrix of W-Cu (70-30 %) shall be produced by PM technique. The sintering shall be carried out in neutral or reducing atmosphere. The ingredient (powders) shall have high purity.</p> <p><b>(b). Cu-Cr Alloy</b></p> <p>Copper : 99 %, Chromium : 1 %.</p> <p>This alloy shall be made using fine alloying practices so as to minimise occlusion of gases. The oxygen content shall not exceed 100 ppm. Vacuum metallurgy for alloying is preferred. The copper used for alloying shall be 99.97 % pure. Electrolytic grade is preferred. Electrical conductivity of Cu-Cr Stem shall be greater than 82 %. (IACS)</p>		
1/2	PSGSG 13-14 / 028		<b>Signature</b>	

PSGSG 13-14 / 028	<b>Product Specifications For FIXED ES CONTACTS</b>	Drg. No.	RDDG 435 0517 2020
		Date	13.02.2014
		Product	<b>GSM 245</b>
<b>5.0</b>	<b>Electron Beam Welding (EBW):</b>  The component shall be finished to size before electron beam welding at the interface. The interface will be between High conductivity copper- Cr alloy and W-Cu Tip. The interface shall be welded to full depth. The welding joint between Cu-Cr alloy and W-Cu tip shall exhibit minimum contact resistance. The Component shall be free from dirt, grease and loose particles.		
<b>6.0</b>	<b>Qualifying Requirements:</b>  The supplier shall be of national / International repute with proven record and should have supplied arcing contacts for electrical applications at least for last three years. The supplier must submit along with the quotation a few references to whom the supplier has supplied a similar material.		
<b>7.0</b>	<b>Tests:</b>  (a). Dimensional : All dimensions shall comply to drawing measures. (b). The component shall be subjected to micro-ohm measurement test, using 100 A DC source and shall measure less than one micro-ohm at the welding interface.		
<b>8.0</b>	<b>Packing :</b>  The contacts shall be packed in high density cardboard boxes, with a primary wrapped in polyethylene and packed individually in dust free boxes after degreasing. The component shall be guaranteed against all manufacturing defects.		
<b>9.0</b>	<b>General :</b>  1. Surface finish of the components shall be at least RA 1.6. 2. The component shall be free from dirt, grease and loose particles.  In case of doubts in drawings or specifications the supplier shall contact BHEL for clarifications.		
2/2	PSGSG 13-14 / 028		<b>Signature</b>

PSGSG/1 3-14/027	<b>Product Specifications For DS MOVING CONTACTS</b>		Drg. No.	RDDG 4 35 0517 2019
			Date	13.02.14
			Product	<b>GSM 245</b>
<b>1.0</b>	<b>Application</b>	:	Movable Arcing rods for Gas Insulated Switchgear Equipment	
<b>2.0</b>	<b>Configuration</b>	:	<ol style="list-style-type: none"> <li>1. Sintered W-Cu (70-30 %), welded (by electron Beam welding process) to the high conductivity copper.</li> <li>2. Machined to drawing dimensions.</li> </ol>	
<b>3.0</b>	<b>Quantity</b>	:	12 No.s	
<b>4.0</b>	<b>Specifications:</b>		<ol style="list-style-type: none"> <li>1. Dimension Drawings : Refer Drg No. RD DG 4 35 0517 2019</li> <li>2. Material: : Tungsten-Copper, ETP copper</li> </ol> <p><b>(a). W-Cu</b></p> <p>A sintered matrix of W-Cu (70-30 %) shall be produced by PM technique. The sintering shall be carried out in neutral or reducing atmosphere. The ingredient (powders) shall have high purity.</p> <p><b>(b). ETP Copper</b></p> <p>ETP copper shall have the following specifications:</p> <ol style="list-style-type: none"> <li>1) The specified copper material shall have minimum conductivity of 95 % IACS. Supplied material will be tested at BHEL for conductivity and the same will be rejected in case they do not meet specified conductivity.</li> <li>2) The material shall be good for brazing, soldering and for electrical applications where high current transfer is involved.</li> </ol>	
1/2	<b>PSGSG/13-14/027.doc</b>		<b>Signature</b>	

PSGSG/1 3-14/027	<b>Product Specifications For DS MOVING CONTACTS</b>	Drg. No.	RDDG 4 35 0517 2019
Date		13.02.14	
Product		<b>GSM 245</b>	
<p><b>5.0</b></p> <p><b>Electron Beam Welding (EBW):</b></p> <p>The component shall be finished to size before electron beam welding at the interface. The interface will be between High conductivity copper and W-Cu Tip. The interface shall be welded to full depth. The welding joint between high conductivity copper and W-Cu tip shall exhibit minimum contact resistance. The Component shall be free from dirt, grease and loose particles.</p> <p><b>6.0</b></p> <p><b>Qualifying Requirements:</b></p> <p>The supplier shall be of national / International repute with proven record and should have supplied arcing contacts for electrical applications at least for last three years. The supplier must submit along with the quotation a few references to whom the supplier has supplied a similar material.</p> <p><b>7.0</b></p> <p><b>Tests:</b></p> <p>(a). Dimensional : All dimensions shall comply to drawing measures.</p> <p><b>8.0</b></p> <p><b>Packing :</b></p> <p>The contacts shall be packed in high density cardboard boxes, with a primary wrapped in polyethylene and packed individually in dust free boxes after degreasing. The component shall be guaranteed against all manufacturing defects.</p> <p><b>9.0</b></p> <p><b>General :</b></p> <p>1. Surface finish of the components shall be at least RA 1.6.</p> <p>2. The component shall be free from dirt, grease and loose particles.</p> <p>In case of doubts in drawings or specifications the supplier shall contact BHEL for clarifications.</p>			
2/2	<b>PSGSG/13-14/027.doc</b>		<b>Signature</b>