



CORPORATE PURCHASE SPECIFICATION

AA 556 19

Rev. No. 03

PREFACE SHEET

SILICA GEL – INDICATING TYPE

FOR INTERNAL USE ONLY
 REMOVE THIS PREFACE BEFORE ISSUE TO SUPPLIERS

Comparable Standards:

INDIAN : IS:3401 - 1992

Suggested/Probable Suppliers and Grades:

1. M/S Patalia Chemicals, Jamnagar : --
2. M/S Minco Products, Chennai : --

Use plant vendor's list.

User Plant References:

1. BHOPAL : PS 54311

Revisions : Cl: 34.11.35 of MOM of MRC-(CPO)			APPROVED : INTERPLANT MATERIAL RATIONALISATION COMMITTEE-MRC (CPO)		
Rev. No. 03	Amd.No.	Reaffirmed	Prepared	Issued	Dt. of 1st Issue
Dt: 15.11.2005	Dt :	Year :2005	BHOPAL	Corp. R&D	June, 1987



CORPORATE PURCHASE SPECIFICATION

AA 556 19

Rev. No. 03

PAGE 1 OF 2

SILICA GEL – INDICATING TYPE

1.0 GENERAL :

This specification governs the quality requirements of Silica Gel – Indicating type, impregnated with cobalt chloride, Coating of cobalt chloride shall not come out easily by rubbing. The material shall be solid with grainy porous structure free from extraneous impurities.

2.0 APPLICATION:

Used as industrial desiccant in packages and transformer breathers.

3.0 COMPLIANCE WITH NATIONAL STANDARDS:

The material shall comply, with the requirements of the following national standard and also meet the requirements of this specification.

IS: 3401-1992, Type: Indicating: Silica Gel

4.0 PARTICLE SIZE:

The standard size of the particle is 3 to 6 mesh (5.6 to 2.8mm).
When checked with 3mm sieve, residue shall be 99.5%, minimum.

5.0 TEST SAMPLES: As per IS:3401.

6.0 PROPERTIES:

When tested in accordance with the relevant clauses of IS:3401, the test sample shall show the following properties.

6.1 Colour: Blue.

6.2 Absorption Capacity of Moisture: 27% by weight, minimum.

6.3 Bulk Density: (For information only): 650±50 g/litre

7.0 TYPE TESTS:

7.1 Loss on drying at 150 + 5°C for 4 hours: 5% by weight, maximum.

Revisions :

Cl: 34.11.35 of MOM of MRC-CPO

APPROVED :

INTERPLANT MATERIAL
RATIONALISATION COMMITTEE-MRC (CPO)

Rev. No. 03

Amd.No.

Reaffirmed

Prepared
BHOPAL

Issued
Corp. R&D

Dt. of 1st Issue
June, 1987

Dt: 15.11.2005

Dt :

Year :2005

AA 556 19	CORPORATE PURCHASE SPECIFICATION	
Rev. No. 03		
PAGE 2 OF 2		

8.0 KEEPING PROPERTY

When stored in covered dry place in the original sealed containers under normal temperature conditions, the material shall retain the properties prescribed in this specification for a period of 12 months after the date of manufacture which shall be subsequent to the date of placement of BHEL order.

9.0 TEST CERTIFICATES:

Unless otherwise specified, three copies of test certificates shall be supplied alongwith each consignment giving the following information.

In addition, the supplier shall ensure to enclose one copy of test certificate along with their dispatch documents to facilitate quick clearance of the material.

AA 556 19, Rev No. 03 : Silica Gel – Indicating type

BHEL Order No.

Manufacture's/Supplier's Name.

Trade mark, if any

Batch/lot No.

Date of manufacture and expiry, if any

Test results of clause 4.0, 6.0 & 7.0.

10.0 PACKING AND MARKING:

The material shall be suitably packed in clean dry polythene bags of at least 100 micron thickness and sealed. These polythene bags shall be further packed in air tight synthetic material containers. The capacity of the containers shall be 5 or 10kg as specified in the BHEL order.

Each consignment shall be legibly marked or labeled with the with the following information:

AA 556 19: Silica Gel – Indicating type

BHEL Order No.

Manufacture's/Supplier's Name.

Trade mark, if any

Batch/lot No.

Date of manufacture and expiry, if any

Sizes and quantity supplied

11.0 REFERRED STANDARDS (Latest Publications Including Amendments):

1. IS:3401