


COPYRIGHT AND CONFIDENTIAL
 The Information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED
 It must not be used directly or indirectly in any way detrimental to the Interest of the company.

	CORPORATE PURCHASING SPECIFICATION	AA 229 01			
		Rev. No. 05			
		PAGE 1 OF 3			
<h2 style="margin: 0;">POLYAMIDE (ARAMID) CALENDER PAPER</h2>					
<p>1.0 GENERAL:</p> <p>This specification governs with the quality requirements calender polyamide (Aramid) paper made from specially formulated polyamide fibres with a high degree of thermal stability. The material is used upto a maximum operating temperature of 220⁰C.</p>					
<p>2.0 APPLICATION:</p> <p>Used as inter-turn insulation, slot liner of electrical machines.</p>					
<p>3.0 COMPLIANCE WITH NATIONAL STANDARDS:</p> <p>There is no national standard covering this type of material.</p>					
<p>4.0 DIMENSIONS AND TOLERANCES:</p>					
<p>4.1 Sizes:</p> <p>Thickness, width and length of the sheet / tape shall be as specified in BHEL order.</p>					
<p>4.1.1 Preferred thickness and Tolerances:</p> <p>0.05, 0.08, 0.13, 0.18, 0.2, 0.25, 0.3, 0.4, 0.5 and 0.8 mm with tolerances as per Annexure I.</p>					
<p>4.1.2 Preferred Width and Tolerances:</p> <p>Sheet: 600mm and 900mm with tolerance of ± 15 mm. Tape: 20, 25 and 30 mm with tolerance of ± 0.5 mm.</p>					
<p>5.0 FINISH:</p> <p>The material shall be free from surface or edge defects, inclusions, voids, pin-holes and cracks which may affect its suitability for use. Visual properties shall be consistent from lot to lot.</p>					
<p>6.0 TEST SAMPLES:</p> <p>A roll of at least 50 metres length for tape or 2 m² sample from inner portion of sheet roll of ordered thickness from the same batch shall be supplied for testing and approval.</p>					
<p>7.0 PROPERTIES:</p> <p>When tested in accordance with the relevant clauses of the test methods mentioned against each, the test samples shall show the following values.</p>					
Revisions : As per 38th MOM of MRC-E		APPROVED : INTERPLANT MATERIAL RATIONALISATION COMMITTEE-MRC (E)			
Rev. No. 05	Amd.No.	Reaffirmed	Prepared	Issued	Dt. of 1st Issue
Dt.:20.04.2012	Dt :	Year :	BHOPAL	Corp. R&D	AUGUST, 1983

AA 229 01

Rev. No. 05

PAGE 2 OF 3

CORPORATE PURCHASING SPECIFICATION



7.1 Physical properties:

7.1.1 Moisture absorption: 8%, maximum

A sample of 75 ± 1 mm x 75 ± 1mm is kept at 90% RH and room temperature (27° ± 2° C) for 72 hours.

8.0 TYPE TESTS:

8.1 Mechanical properties

:

Breaking strength

: As per Annexure I

Elongation at break

: As per Annexure I

8.2 Electrical Properties:

Electrical strength (BDV) in air at 27 ± 2° C

: As per Annexure I

Volume Resistivity (ASTM D -257)

: 1 x 10¹⁶ ohm-cm, minimum.

9.0 ACCEPTANCE CRITERIA:

Material shall be accepted on the basis of the following:

- a) Compliance certificate furnished by the supplier
- b) Test certificate furnished by the supplier and / or testing carried out at BHEL end.

10.0 TEST CERTIFICATES:

Unless otherwise stated, three copies of test certificates shall be supplied along with each consignment giving following information:

In addition, the supplier shall ensure to send one copy of test certificate along with the dispatch documents to facilitate quick clearance of the materials.

AA 229 01, Rev 05: Polyamide (Aramid) calender paper.

BHEL order No.

Manufacturers/suppliers Name:

Trade name/mark, if any:

Batch/Lot No.

Quantity supplied

Test results of clauses 4.0, 7.0 and 8.0

11.0 PACKING AND MARKING:

Rolls shall be suitably packed to prevent damage during transit and storage.

Each consignment shall be legibly marked or labeled with the following information:

AA 229 01: Polyamide (Aramid) calender paper

BHEL order No.

Manufacturers/suppliers Name:

Batch/Lot No.

Trade mark, if any

Sizes and Quantity supplied

12.0 REFERRED STANDARDS (Latest Publications Including Amendments):

- 1) ASTM D 257

ANNEXURE I - CLAUSE 8.0

Nominal Thickness, mm	Tolerance ± mm	Substance g/m ² Tolerance of ±10%	Breaking strength , N/cm width, minimum		Elongation, percent, minimum		Tear strength, N, minimum		Dissipation factor, maximum	Electric strength (BDV) in air at 27±2°C kV/mm, min.
			Machine direction (MD)	Cross machine direction (XD)	Machine direction (MD)	Cross machine direction (XD)	Machine direction (MD)	Cross machine direction (XD)		
0.05	0.01	40	44	19	11	8	0.7	1.6	0.004	19
0.08	0.01	63	70	35	11	9	1.2	2.3	0.005	24
0.13	0.02	120	140	68	16	13	2.4	5.1	0.006	27
0.18 0.2	0.02	170	230	120	19	15	3.6	7.1	0.006	35
0.25	0.03	250	320	160	20	16	5.2	9.8	0.006	33
0.3	0.03	310	390	210	23	19	6.5	12	0.007	34
0.4	0.05	410	490	260	21	17	8.1	15	0.007	33
0.5	0.06	540	670	390	22	17	12	19	0.007	33
0.8	0.10	850	910	610	20	16	--	-	0.007	28



CORPORATE PURCHASING SPECIFICATION

AA 229 01

Rev. No. 05

PAGE 3 OF 3