



**CORPORATEPURCHASINGSPECIFICATION**

AA55307

Rev No.01

PREFACE SHEET

**SILICONE RELEASING COMPOUND**

FOR INTERNAL USE ONLY  
REMOVE THIS PREFACE BEFORE ISSUE TO SUPPLIERS

**Equivalent/Comparable Standards:**

**User Plants and Replaced Plant Specifications/References:**

Bhopal : MCB 6039

**COPYRIGHT AND CONFIDENTIAL**  
The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED.  
It must not be used directly or indirectly in any way detrimental to the interest of the company.

**Revisions:**  
As per clause 44.3.a) of MOM of MRC-CPO+NM

**APPROVED:**  
INTERPLANT MATERIAL RATIONALISATION  
COMMITTEE – MRC(CPO+NM)

Rev No.01

Amd No.

Reaffirmed

Prepared  
HEP, Bhopal

Issued  
Corp.R&D

Dt. of 1<sup>st</sup> Issue  
01-01-1985

Dt:01-06-1992

Dt:

Year:2015

**This page intentionally left blank**



## CORPORATE PURCHASING SPECIFICATION

AA55307

Rev No. 01

PAGE 1 of 2

### SILICONE RELEASING COMPOUND

#### 1 GENERAL

This specification governs the quality of non-melting, translucent silicone compound having a consistency as that of petroleum jelly and retaining essentially the same consistency up to a temperature of 205°C. It shall be heat stable, oxidation-resistant and inert towards metals and plastic materials. It shall be insoluble in water, glycerol and mineral oils.

#### 2 APPLICATION

Used as a parting fluid/releasing agent.

#### 3 COMPLIANCE WITH NATIONAL STANDARDS

There is no Indian Standard covering this material.

#### 4 TEST SAMPLES

0.5 kg of sample shall be supplied for testing and approval.

- 4.1 To draw a representative sample, the contents of the container selected for sampling shall be mixed as thoroughly as possible by shaking or stirring or both or by rolling, so as to bring all portions into uniform distribution.
- 4.2 The samples shall be taken in a suitable, clean, dry air-tight glass bottle of one litre capacity. It should be almost but not completely filled by the sample.
- 4.3 In case of failure of first sample, two samples shall be drawn from other two drums of the same consignment at random and failure of the second sample in complying with the specification will lead to the rejection of the whole consignment.

#### 5 PROPERTIES

##### 5.1 Colour

Colourless, translucent

##### 5.2 Flash Point

Not below 330°C

##### 5.3 Consistency

Soft Greasy

#### 6 SHOP TEST

When applied on the moulds during manufacture of moulding components, the material should release laminates, potting etc. at the processing temperature and time.

#### Revisions:

As per clause 44.3.a) of MOM of MRC-CPO+NM

#### APPROVED:

INTERPLANT MATERIAL RATIONALISATION  
COMMITTEE – MRC(CPO+NM)

Rev No.01

Amd No.

Reaffirmed

Prepared  
HEP, BhopalIssued  
Corp.R&DDt. of 1<sup>st</sup> Issue  
01-01-1985

Dt:01-06-1992

Dt:

Year:2015

**7 TEST CERTIFICATES**

Unless otherwise stated, three copies of test certificates shall be supplied along with each consignment giving the following information:

AA55307 (Rev. No. 01): SILICONE RELEASING COMPOUND

BHEL Order No.

Manufacturer's/Supplier's Name

Trade mark, if any,

Batch/Lot No.

Quantity supplied

Date of Manufacture & Expiry

Test results of clauses 5

**8 PACKING & MARKING**

The material shall be supplied in tubes or in containers of suitable capacity as per the order.

Each container should bear the following information

AA55307: SILICONE RELEASING COMPOUND

BHEL Order No.

Manufacturer's/Supplier's Name

Trade Mark, if any

Date of Manufacture & Expiry

Quantity supplied

**9 ENVIRONMENTAL REQUIREMENTS**

The supplier shall furnish Material Safety Data Sheet (MSDS) covering all information relating to human safety and environmental impacts of the hazardous materials particularly during their transportation, storage, handling and disposal along with each supply.

Each container shall be marked with corresponding symbol and minimum worded cautionary notice for flammable / corrosive / toxic / harmful / irritant and oxidizing etc. as applicable.

**10 REFERRED STANDARDS (Latest Publications Including Amendments)**

NIL