



TSD 6206 A

**PLANT PURCHASING SPECIFICATION****BHOPAL****BP 56179** 160

Rev. No. 01

PAGE 1 OF 6

SUPERSEDES  
BP 56179 Rev 00**CHEMICAL AND THERMAL RESISTANT EPOXY ENAMEL  
(BASE & CATALYST)**  
-----**1. GENERAL:**

This specification covers the technical requirements of two pack epoxy enamel which gives tough, flexible, glossy finish with excellent moisture & heat resistance and good durability in chemical atmosphere.

**2. APPLICATION:**

Suitable for application by brushing or spraying on Transformers, Radiators etc. which are subsequently subjected to vapour phase treatment.

**3. COMPLIANCE WITH NATIONAL STANDARDS:**

There is no Indian Standard covering this material.

**4. COLOUR:**

Shall be specified in our order.

**5. FINISH:**

Smooth and full glossy.

**6. FREEDOM FROM DEFECTS:**

The paint shall remain free from defects like hard settling of pigments, skinning when kept in closed container and livering (excessive viscosity build up) during its rated shelf life.

The dried paint film shall be free from defects like bittyness, floating of pigments, surface haze, orange peeling, colour fading, wrinkles, etc.

Revision : 1. Reviewed & Reaffirmed  
2. Brought upto date

Issued by : *P. N. Ramamurthy*  
STANDARDS AND MATERIALS GROUP  
TECHNICAL SERVICES DEPARTMENT

Rev. No. : 01

Date : 28.10.95

Date of first issue : Dec. 1985



TSD 6207A

## PLANT PURCHASING SPECIFICATION

BHOPAL

BP 56179 (159)

Rev. No. 01

PAGE 2 OF 6

## 7. CHEMICAL COMPOSITION:

The material shall be based on two component epoxy system suitably pigmented base and accelerator. The mixing ratio of the base and accelerator shall be as per supplier's recommendation. The type and content of the binding material as determined by IR spectrography shall be strictly adhered to the "Type Approved Sample".

## 8. TEST SAMPLES:

Tender samples will not be required when once the type approval (Clause 12) is given and the supplier concerned declares that the material for which the tender is given is of the same quality as the type approved sample.

Representative samples of the material shall be drawn and treated as prescribed under Clause 3 of IS:101.

## 9. TEST METHOD

Unless otherwise specified material shall be tested in accordance with IS:101.

## 10. PROPERTIES ON BASE AND CATALYST MIX:

Base and Catalyst mix (as per supplier's recommendations), when tested in accordance with IS:101 IS:2074, Defence specification DEF 1053 and Appendices 1 & 2 to this specification, shall have the properties as below:

10.1 Specific Gravity at 25 ± 2 deg.C

1.2 ± 0.2

10.2 Drying Time

Surface dry : 2 hours, Max.

Hard dry : 16 hours, Max.

Tack free : 24 hours, Max

10.3 Consistency

40 to 70 seconds 25 ± 2 deg.C in FC4 Cup.

10.4 Fineness of Grind

6 minimum on Hegman's gauge.

10.5 Gloss

90 percent, Minimum.



TSD 6207 A

## PLANT PURCHASING SPECIFICATION

BHOPAL

BP 56179

158

Rev. No. 01

PAGE 3 OF 6

**10.6 Scratch Hardness On Mild Steel Panel**

After the paint film is cured for 7 days at ambient temperature and tested under a load of 2,000 g, no such scratch as to show the bare metal shall be produced.

**10.7 Flexibility and Adhesion**

The paint film shall not show sign of damage, detachment or cracking when tested after 7 days curing at ambient temperature.

**10.8 Resistance to Salt Spray (Cl.5.2. IS:2074)**

The panel prepared from the material shall show no signs of corrosion after continuous exposure for 7 days in Salt Spray Cabinet.

**10.9 Impact Test (Defence Spec. 1053)**

The film shall not show any sign of damage.

**10.10 Resistance to transformer oil at 90 deg.C  $\pm$  2 deg.C for 48 hrs**

Shall not show any sign of deterioration.

**10.11 Chemical & Thermal Resistance Test (Appendix - I) Type Test**

Panels prepared and tested in accordance with Appendix-1 to this specification, when kept in the SHELLSOL-H (or equivalents) vapour at the specified temperature & time, shall not show any sign of deterioration.

**10.12 Pot Life (Appendix-2)**

8 to 24 hours.

**11. PROPERTIES ON BASE ENAMEL:****11.1 Pigment And Non-Volatile Matter Content**

60 percent, Min (by weight of the base paint).

**11.1.1 Pigment:**

15 percent, Min. (by weight of the base paint)

**11.1.2 Epoxy Resin Content:**

30 percent, Min. (by weight of the base paint after finding the pigment and non-volatile matter content).



TSD 6207 A

## PLANT PURCHASING SPECIFICATION

BHOPAL

BP 56179

157

Rev. No. 01

PAGE 4 OF 6

## 12. TYPE APPROVAL:

12.1 Samples:

Samples for Type Approval testing shall be accepted only from those manufacturers whose manufacturing and testing facilities are considered satisfactory to ensure continuous supply of good product.

12.2 Type Test:12.2.1 Outdoor durability test (Annexure-D, IS 2932-1993)

Painted panels prepared as per Annexure D, but with the primer and finish paints as per this specification and tested as per D-3 of IS:2932-1993 shall satisfy the requirements laid down D 3.3 for at least 12 months after painting.

## 13. KEEPING PROPERTY:

When stored in a covered dry place in the original sealed containers under normal temperature conditions, the base and accelerator when mixed in appropriate proportions shall retain the properties prescribed in this specification for a period of at least 12 months after the date of manufacture which shall be subsequent to the date of placing the order.

## 14. INSPECTION AT SUPPLIER'S WORKS:

Whenever specified, tests and inspections are to be conducted in the presence of BHEL's representative.

The supplier shall offer BHEL's representative all reasonable facilities, without charge to satisfy the later that the material is being furnished in accordance with this specification. The supplier shall prepare and provide necessary test specimens for testing to be carried out at his premises. If facilities are not available at his works, the supplier shall make necessary arrangements for carrying out the prescribed tests elsewhere. The supplier shall notify BHEL in advance about the readiness of the material for inspection and testing.

BHEL reserves the right to test the material at BHEL's works and the final acceptance of the material shall be based on these test results.

## 15. TEST CERTIFICATES:

Unless otherwise stated, three copies of Test Certificates shall be supplied giving the following information:

In addition the supplier shall ensure to enclose one copy of Test Certificate along with their despatch document to facilitate quick clearance of the material.



TSD 6207 A

## PLANT PURCHASING SPECIFICATION

BHOPAL

BP 56179 <sup>156</sup>

Rev. No. 01

PAGE 5 OF 6

BP 56179: Chemical and Thermal Resistant Epoxy Enamel  
Rev.01 (Base & Catalyst)

BHEL Order No.

Supplier's Name & Trade Mark, if any.

Batch No.

Date of Manufacture and Expiry

Test Results of Clauses 10 & 11.

16. PACKING AND MARKING:

Unless otherwise stated, base and accelerator shall be packed separately in steel containers of appropriate capacities.

Each container shall bear the following information:

BP 56179: Chemical and Thermal Resistant Epoxy Enamel  
(Base & Catalyst)

BHEL Order No.

Manufacturer's/Supplier's Name.

Trade Mark, if any.

Batch No.

Date of Manufacture and Expiry

Quantity.

17. REJECTION AND REPLACEMENT:

If the material does not comply with the requirements of this specification during receipt inspection at BHEL or if any defect is found during further processing of the material, BHEL reserves the right to reject the whole consignment not withstanding any previous certification of satisfactory testing and/or inspection. The supplier shall undertake to replace the rejected material at his own cost and the rejected material shall be taken back by the supplier after fulfilling all the commercial terms and conditions.



TSD 6207 A

## PLANT PURCHASING SPECIFICATION

BHOPAL

BP 56179

Rev. No. 01

PAGE 6 OF 6

155

APPENDIX - ICHEMICAL AND THERMAL RESISTANCE TESTS (Clause 9.11)

Take a panel of 25 x 100 mm CR Sheet Steel, emery and degrease with xylol to remove dirt, oil and grease, if any. Apply a coat of epoxy finishing paint and allow to air dry. Apply a second coat of epoxy paint to get uniform coating and allow to dry for 72 hours. Weigh the painted panel and expose the panel in the chamber of SHELLSOL-H vapours at 130 deg.C under vacuum in TRM-micafil VPI plant for 72 hrs. At the end of 72 hrs take out the panel from the chamber and observe for any deterioration in paint film i.e. blisters, paintfilm softening and colour change etc. and weight the panel again. The paint passes the test if no discolouration in paint film takes place and weight loss is not more than 50 mg.

APPENDIX-2DETERMINATION OF POT LIFE (Clause 9.12)

About 100 ml of the mixed paint prepared by mixing the base and accelerator in the recommended proportions is taken in a beaker. The paint shall be such that it should be usable by brush under a specified pot life of 8-24 hours at room temperature.

In order to see if the paint has gelled or not, a small quantity of the mixed paint is dissolved in the recommended thinner. It should not dissolve if the paint has gelled and vice-versa.